



Version: 1	Date: 27.05.2019	
<b>Test Report 69635</b>		
Created by: Dr. Heumüller-Klug	Page 2 of 3	
	Appendix:	

**1. Fabric samples:** Cloth PES 70% / PA 30% orange



**2. Domestic washing and drying procedures for textile testing (ISO 6330:2012)  
DIN EN ISO 6330:2013-02**

Washing machine:	Typ „A1“; Electrolux FOM CLS 71
Washing process:	6N, normal
Temperature:	60 °C
Detergent:	Reference detergent 3 (ECE- Reference detergent 98)
Total wash load:	2 kg
Ballast:	Typ III, 100% Polyester
Drying process:	F – Tumbler
Cycle:	3